

## TECHNICAL DATA SHEET

## GP.PPC 2228-1015-HF BK01

Polypropilene Copolymer

Material: PP Copo Alloy General Purpose

Color: Black

**Description:** Reprocessed

**Grade:** Invection Moulding

Property	Condition	Range	Unit	Test Method
General Properties				
Specific Gravity	23°C	0.95 to 1.05	Gr/cm3	Own Methode
Melt Flow Rate	230°C/2.16 Kg	22.00 to 28.00	Gr/10 min.	ASTM D1238
Ash		10 to 15	%	<b>ASTM D2584</b>
% Moisture	23°C	0.01 to 0.05	%	ASTM D570
Gloss Level		to	Level	Own Methode
Mechanical Properties				
Izod Impact Notched	23°C	1.00 to 5.00	Ft-Lb/In.	ASTM D256
Torsion	23°C	50 to	Lb-in	Own Methode
Flexural Strength	23°C	30.00 to 40.00	MPa	ASTM D790

All data given are typical product data and does not represent minimum values.

The actual value may vary depending on color and additives.

The information provided above is based on our internal revision procedures and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use. Globa plast de Mexico S de RL de CV. will not be liablefor any injury or damage arisingfrom the application of this information.

Globa Plast de Mexico, S. de RL. de CV.

Ave. 2 No.-188, Col. Central de Carga. San Nicolas de lo Garza, N.L. Mex. Tel. 81-8351-0774

<sup>\*</sup>MATERIALS MUST BE DRIED PRIOR TO PROCESSING