



TECHNICAL DATA SHEET

GP.PPC 1020-T0010 BK01

Polypropilene Copolymer with up to 10% talc

Material:	PP Copo Alloy General Purpose
Color:	Black
Description:	Reprocessed
Grade:	Injection Moulding

Property	Condition	Range	Unit	Test Method
<i>General Properties</i>				
Specific Gravity	23°C	0.90 to 0.99	Gr/cm3	Own Methode
Melt Flow Rate	230°C/2.16 Kg	10.00 to 20.00	Gr/10 min.	ASTM D1238
Ash	-----	0 to 10	%	ASTM D2584
% Moisture	23°C	0.01 to 0.05	%	ASTM D570
Gloss Level	-----	----- to -----	Level	Own Methode
<i>Mechanical Properties</i>				
Izod Impact Notched	23°C	1.00 to 3.00	Ft-Lb/In.	ASTM D256
Torsion	23°C	60 to -----	Lb-in	Own Methode
Tensile Strength (Yield)	23°C	20.00 to 30.00	MPa	Own Methode
Flexural Strength	23°C	30.00 to 40.00	MPa	ASTM D790
Flexural Modulus	23°C	1100 to 1400	MPa	ASTM D790

***MATERIALS MUST BE DRIED PRIOR TO PROCESSING**

All data given are typical product data and does not represent minimum values.
The actual value may vary depending on color and additives.

The information provided above is based on our internal revision procedures and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use. Globo plast de Mexico S de RL de CV. will not be liable for any injury or damage arising from the application of this information.

Globo Plast de Mexico, S. de RL. de CV.

Ave. 2 No.-188, Col. Central de Carga. San Nicolas de lo Garza, N.L. Mex. Tel. 81-8351-0774