



TECHNICAL DATA SHEET

GP.PMMA 0308 CR01

Acrylic, Polymethyl Methacrylate

Material:	PMMA General Purpose
Color:	Crystal
Description:	Reprocessed
Grade:	Injection Moulding

Property	Condition	Range	Unit	Test Method
<i>General Properties</i>				
Specific Gravity	23°C	1.15 to 1.20	Gr/cm ³	Own Methode
Melt Flow Rate	230°C/3.80 Kg	3.00 to 8.00	Gr/10 min.	ASTM D1238
Ash	-----	----- to -----	%	ASTM D2584
% Moisture	23°C	0.01 to 0.05	%	ASTM D570
Gloss Level	-----	----- to -----	Level	Own Methode
<i>Mechanical Properties</i>				
Izod Impact Unnotched	23°C	3.50 to 6.00	Ft-Lb/In.	ASTM D4812
Torsion	23°C	----- to -----	Lb-in	Own Methode

***MATERIALS MUST BE DRIED PRIOR TO PROCESSING**

All data given are typical product data and does not represent minimum values.
The actual value may vary depending on color and additives.

The information provided above is based on our internal revision procedures and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use. Globo plast de Mexico S de RL de CV. will not be liable for any injury or damage arising from the application of this information.

Globo Plast de Mexico, S. de RL. de CV.

Ave. 2 No.-188, Col. Central de Carga. San Nicolas de lo Garza, N.L. Mex. Tel. 81-8351-0774